

HOME COUNTIES PLAINS CONSTRUCTION SPECIFICATION

	CONSTRUCTION	42oz	50oz
	MACHINE GAUGE	1/10th Gauge	1/10th Gauge
	PILE HEIGHT	7 mm	8 mm
	TUFT DENSITY	155,000 tufts/m ²	170,500 tufts/m ²
	PILE WEIGHT	1,423 gms/m ²	1,695 gms/m ²
	TOTAL CARPET WEIGHT	42 oz/yd ²	50 oz/yd ²
	CARPET THICKNESS	2,203 gms/m ²	2,475 gms/m ²
	WIDTH	9.9 mm	10.9mm
		4 & 5 metre	4 & 5 metre
	COMPOSITION	80% Wool 10% Polypropylene 10% Tuftbond Woven Polypropylene Woven Secondary	80% Wool 10% Polypropylene 10% Tuftbond Woven Polypropylene Woven Secondary
 	PERFORMANCE	Extra Heavy Domestic Exceeds 21,500 Rubs 31.5% Thickness loss after 24 hrs recovery 27.9% Thickness loss after 1,000 impacts Above 1 kg	Extra Heavy Domestic / Medium Contract Exceeds 50,000 Rubs 25.5% Thickness loss after 24 hrs recovery 22.5% Thickness loss after 1,000 impacts Above 1 kg
	COLOUR FASTNESS	4/5 on all colours 4/5 on all colours 4/5 on all colours	4/5 on all colours 4/5 on all colours 4/5 on all colours
	THERMAL VALUE	1.4 Tog 0.14 m ² k/w	1.5 Tog 0.15 m ² k/w
	FLAMMABILITY	Dfl,S1 Pass Pass - Low radius of ignition	Dfl,S1 Pass Pass - Low radius of ignition
	CHEMICAL IMPACT	E1 Compliant	E1 Compliant
	BIOLOGICAL ATTACK	Eulan Treated	Eulan Treated

GENERAL INFORMATION

Installation - In all contract locations an 'all-over' stick down method is recommended to BS 5325 (1983). If underlay is required it should be of a firm and unyielding type. For quantity orders requiring colour matching, please state at time of ordering.

Maintenance - To maintain your carpet's appearance it is recommended that it is vacuumed at least three times per week, to remove particles of dirt and dust. An upright vacuum with beater bar and brush is recommended for use with cut pile carpets. Please note, over time, regular foot traffic will flatten the pile surface in the main walkways, causing areas of differential wear. These areas will appear lighter or shaded in comparison to the less frequently used parts. This shading / tracking or flattening happens to all carpets with a pile surface and as such is not accepted as the basis for any complaint. Similarly Pile Reversal (or watermarking) is a phenomenon that can affect all cut pile carpets and as such is not accepted as a manufacturing fault.

Matching - This sample may not be from the same production batch as current stock and therefore should be used as a guide and not as an exact match. Equally matching between 5 metre and 4 metre widths cannot be guaranteed.

Important - Minimum order length is 1.5 metres.

February 2014



GREENWOOD & COOPE LTD. BROOKHOUSE MILL, GREENMOUNT, BURY, LANCASHIRE BL8 4HR
TEL: 01204 881234 FAX: 01204 887722
E-MAIL: info@cormarcarpets.co.uk WEBSITE: www.cormarcarpets.co.uk

